



Complex permeability vs. Frequency



Initial permeability	μ_i	25°C	1300±20%
Saturation magnetic	Bs(mT)	25°C	240
Relative temperature coefficient		20~40°C	±3%
Relative temperature coefficient		>10°C	±5%
Temperature stability			±0.5%
Density			7.250
Test core	toroid(mm)		φ30×1.5



Initial permeability vs. Temperature



Flux density vs. Temperature

